



B_s - Temperature


Initial permeability	μ_i	25°C	4000±25%
Saturation magnetic flux density	B_s (mT)	25°C	550
Residual magnetic flux density	B_r (mT)	25°C	90
Coercive field strength	H_c (A/m)	25°C	15



μ_i - Temperature



μ_i - Frequency



B - H

