





/Material:

/Features:

1. / Low Core Loss and High Saturation Flux Density
2. 100 / The Temperature Point of the Lowest Core Loss is 100



Initial permeability	$\mu_i$	25°C	2500±25%
Saturation magnetic flux density	Bs(mT)	25°C	520
		100°C	410
Remanence	Br(mT)	25°C	210
		100°C	60
Coercivity	Hc(A/m)	25°C	14
		100°C	7
Core loss	Pcv(kW/m³)	25°C	600
		60°C	400
		100°C	250



/Material:

