


Bs-Temperature

H=1194A/m



Initial permeability	μ	25°C	2000±25%
Saturation magnetic flux density	Bs(mT)	25°C	520
		100°C	410
		25°C	135

Coercivity	Hc(A/m)	25°C	13
		100°C	7
Core loss	Pcv(kW/m³)	25°C	650
		100°C	300

Curie temperature	Tc(°C)	232
Electrical resistivity	$\rho(\Omega\cdot m)$	6.5

